CLASS 1

Building Product Information Sheet

Product Name:

Zincalume Soft Edge Angle Flashing

Product Descriptions and its intended use:

Zincalume Soft Edge Angle Flashings are to stop water ingress at roof and wall junctions.

Key technical specifications

* Material : Zincalume
* Thickness : 0.55 mm

Product identifier(s):

44051,44062,44065

Place of Manufacture: ☒ Aotearoa New Zealand ☐ Overseas

Legal and trading name of manufacturer(s)

Sigma Sheetmetal Products Ltd

Address for service:

STREET NAME:	24 Princes Street	SUBURB:	Onehunga
CITY, COUNTRY:	Auckland, New Zealand	POSTCODE:	1061

Website:	http://www.sigmasheet.co.nz
Email Address:	Sales@sigmasheet.co.nz
Phone no.:	09 636 3657
NZBN:	9429038071027

Relevant Building Code clauses:

- B2 Durability: Performance clauses B2.3.1(a) (ii) (iii)
- E2 External Moisture: Performance clause E2.3.2

Statement on how the building product is expected to contribute to compliance:

B2.3.1 (a) (ii) and (iii). Zincalume Soft Edge Angle Flashings have a durability of at least 50 years where the flashings are installed and maintained correctly. Refer to the design and installation requirements for further information.

E2.3.2 Zincalume Soft Edge Angle Flashings will prevent water ingress at junctions of a roof and wall by the use of a malleable soft edge, an upturn and hem

• options for compliance set out in section 19 of the Act (regulations, acceptable solution, verification method)

• standard or technical document that describes the performance of the building product or the relevant specifications to which the building product was manufactured

• physical properties of the building product

• how the building product is intended to be used

Limitations on the use of the building product:

Refer to Tables 20, 21 & 22 in E2/AS1 for materials that galvanised steel is suitable to be in contact with and have water run off.

Not suitable for Zone D - sea-spray zone. Refer to Section 4 of NZS 3604 : 2011 for definition of sea-spray zones.

Not suitable for Galvanised Steel corrugated roof

Design requirements that would support the use of the building product:

Used with galvanised steel roof

Refer to E2/AS1 Section 4.6 table 7 : Roof or deck to wall and Section 8.4 Figure 48 for flashing dimension requirements

Installation requirements:

Refer to E2/AS1 Section 8.4 Figure 48 for installation information

Clean the flashing with warm soapy water to remove any residue oils used during the manufacturing process, rinse off the cleaning agent with water and allow to dry.

Use an appropriate chemical metal etch primer to paint all surfaces prior to installing the flashings.

Use heavy zinc or zinc-tin coated nails to secure the flashing but avoid nailing through the flashing

Apply two coats of top coat to the flashing

Maintenance requirements

Manual washing is required to prevent the accumulation of dirt, debris or other material not removed by rain. Walls should be washed:

- every 6 months in severe environments; and
- every 12 months in moderate environments.

Areas that do not receive adequate or any rain washing such as soffits, wall cladding under eaves, the underside of gutters, fascias, sheltered areas of garage doors, and unwashed roof areas: should be washed:

- every 3 months for severe environments; and
- every 6 months for moderate environments.

Is the building product / building product line subject to a warning or ban under section 26?:

☐Yes ☒No

If yes, description of the warning or ban under section 26:

Date: 15/11/2023